










Eramosa - Technical information

Tile collection performance based on industry standards.

Technical Information

	WATER ABSORPTION	ANSI / ISO - (%)	< 0.5%
	ABRASION RESISTANCE	ANSI / ISO	CLASS 4
	SCRATCH HARDNESS	ANSI / ISO - (Mohs)	MATTE 7 POLISHED 6
	BREAKING STRENGTH	ANSI - (lbf) ISO - (N)	≥300 >1300
	SHADE VARIATION		V2
	SLIP RESISTANCE	ANSI - DCOF (WET) ISO - R VALUE	MATTE ≥0.50 MATTE R (-) POLISHED <0.42 POLISHED R (-)
	CHEMICAL RESISTANCE	ANSI / ISO	MATTE CLASS A POLISHED CLASS B
	STAIN RESISTANCE	ANSI ISO	MATTE CLASS A MATTE CLASS 5 POLISHED CLASS B POLISHED CLASS 4
	FROST RESISTANCE	ANSI / ISO	PASS

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Porcelain tile P1 Class, ISO 13006 - G - Bia Group, En 14411 - G - Bia Group. Variances in test values can occur in different production lots.

Usage recommendation

Anatolia's recommendations for suitable applications.

Usage Recommendations*		MATTE GLAZED PORCELAIN		POLISHED GLAZED PORCELAIN	
		WALL	FLOOR	WALL	FLOOR
INTERIOR	RESIDENTIAL	•	•	•	•
	COMMERCIAL	•	•	•	•
	HEAVY COMMERCIAL	•		•	
EXTERIOR	RESIDENTIAL / COMMERCIAL	•		•	

* These recommendations are not defined by ANSI/ISO standards.