

Huxley – Technical information

Collection performance based on industry standards.

Technical Information

	WATER ABSORPTION	ANSI / ISO - (%)	<0.1%
	ABRASION RESISTANCE	ANSI / ISO	ORGANIC MATTE <120mm³
	BREAKING STRENGTH	ANSI - (lbf) ISO - (N)	9 mm ≥570 ≥2600
	SHADE VARIATION		V3
	SLIP RESISTANCE	ANSI DCOF (WET) ISO - R VALUE	ORGANIC MATTE ≥0.60 (ID, IW, IW+, EW*, O/G*) ORGANIC MATTE R10
	CHEMICAL RESISTANCE	ANSI / ISO	ORGANIC MATTE CLASS A
	STAIN RESISTANCE	ANSI / ISO	ORGANIC MATTE CLASS A / CLASS 5
	FROST RESISTANCE	ANSI / ISO	PASS

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Impervious (Porcelain) P1 Class,
ISO 13006 - G - BI_g Group, En 14411 - G - BI_g Group. Variances in test values can occur in different production lots.

Usage recommendation

Anatolia’s recommendations for suitable applications.

Usage Recommendations*		ORGANIC MATTE	
APPLICATION		WALL	FLOOR
INTERIOR	RESIDENTIAL	•	ID, IW, IW+, EW*, O/G*
	COMMERCIAL	•	ID, IW, IW+, EW*, O/G*
	HEAVY COMMERCIAL	•	ID, IW, IW+, EW*, O/G*
EXTERIOR	RESIDENTIAL / COMMERCIAL	•	ID, IW, IW+, EW*, O/G*

* These are Anatolia recommendations for suitable applications. They are not defined by ANSI / ISO Standards.
DCOF Classifications per ANSI A326.3: (ID): Interior, Dry (IW): Interior, Wet (IW+): Interior, Wet Plus (EW): Exterior, Wet (O/G): Oils/Greases