










# Mayfair - Technical information

Tile collection performance based on industry standards.

## Technical Information

	WATER ABSORPTION	ANSI / ISO - (%)	< 0.5%
	ABRASION RESISTANCE	ANSI / ISO	CLASS 4
	SCRATCH HARDNESS	ANSI / ISO - (Mohs)	POLISHED 5      MATTE 6
	BREAKING STRENGTH	ANSI - (lbf) ISO - (N)	≥500 >2200
	SHADE VARIATION		V2
	SLIP RESISTANCE	ANSI - DCOF (WET) ISO - R VALUE	POLISHED <0.42      MATTE ≥0.42 POLISHED R (-)      MATTE R (-)
	CHEMICAL RESISTANCE	ANSI / ISO	CLASS A
	STAIN RESISTANCE	ANSI ISO	CLASS A CLASS 5
	FROST RESISTANCE	ANSI / ISO	PASS

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Porcelain tile P1 Class, ISO 13006 - G - Bia Group, En 14411 - G - Bia Group. Variances in test values can occur in different production lots.

## Usage recommendations

Anatolia's recommendations for suitable applications.

Usage Recommendations*		POLISHED GLAZED PORCELAIN		MATTE GLAZED PORCELAIN	
		WALL	FLOOR	WALL	FLOOR
INTERIOR	RESIDENTIAL	•	•	•	•
	COMMERCIAL	•	•	•	•
	HEAVY COMMERCIAL	•		•	
EXTERIOR	RESIDENTIAL / COMMERCIAL	•		•	

\* These recommendations are not defined by ANSI/ISO standards.