










Prima - Technical information, *Glazed Porcelain, True White Color Only*

Tile collection performance based on industry standards.

Technical Information <i>Glazed Porcelain, True White Color Only</i>			POLISHED	MATTE
	WATER ABSORPTION	ANSI / ISO - (%)	< 0.5%	
	DEEP / ABRASION RESISTANCE	ANSI / ISO	4	
	SCRATCH HARDNESS	ANSI / ISO - (Mohs)	6	
	BREAKING STRENGTH	ANSI - (lbf) ISO - (N)	≥450 ≥2000	
	SHADE VARIATION		V1	
	SLIP RESISTANCE	ANSI - DCOF (WET) ISO - R VALUE	POLISHED ≥0.42 DRY (ID) POLISHED R (-)	MATTE ≥0.42 (ID, IW) MATTE R (-)
	CHEMICAL RESISTANCE	ANSI / ISO	CLASS A	
	STAIN RESISTANCE	ANSI ISO	CLASS B CLASS 4	CLASS A CLASS 5
	FROST RESISTANCE	ANSI / ISO	PASS	

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Porcelain tile P1 Class, ISO 13006 - G - Bia Group, En 14411 - G - Bia Group. Variances in test values can occur in different production lots.

Usage recommendations

Anatolia's recommendations for suitable applications.

Usage Recommendations*, <i>True White</i>		POLISHED GLAZED PORCELAIN		MATTE GLAZED PORCELAIN	
APPLICATION		WALL	FLOOR	WALL	FLOOR
INTERIOR	RESIDENTIAL	•	ID	•	ID, IW
	COMMERCIAL	•	ID	•	ID, IW
	HEAVY COMMERCIAL	•		•	
EXTERIOR	RESIDENTIAL / COMMERCIAL	•		•	










* These recommendations are not defined by ANSI/ISO standards.

DCOF Classifications per ANSI A326.3: (ID): Interior, Dry (IW): Interior, Wet (IW+): Interior, Wet Plus (EW): Exterior, Wet (O/G): Oils/Greases

* Factors other than the noted DCOF result must also be taken into consideration. Such factors include, but are not limited to, expected contaminants, drainage, surface texture, effect of structure on the DCOF measurement, number of grout joints, traction-enhancing features, and intended use in addition to the other criteria noted in standard ANSI A326.3

Prima - Technical information, *Unglazed Porcelain*

Tile collection performance based on industry standards.

Technical Information Unglazed Porcelain		MATTE	
	WATER ABSORPTION	ANSI / ISO - (%)	< 0.5%
	DEEP / ABRASION RESISTANCE	ANSI / ISO	136
	SCRATCH HARDNESS	ANSI / ISO - (Mohs)	9
	BREAKING STRENGTH	ANSI - (lbf) ISO - (N)	≥ 500 ≥ 2200
	SHADE VARIATION		V1
	SLIP RESISTANCE	ANSI - DCOF (WET) ISO - R VALUE	MATTE ≥0.42 (ID, IW) MATTE R (-)
	CHEMICAL RESISTANCE	ANSI ISO	CLASS A
	STAIN RESISTANCE	ANSI ISO	CLASS A CLASS 5
	FROST RESISTANCE	ANSI / ISO	PASS

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Porcelain tile P1 Class, ISO 13006 - G - Bia Group, En 14411 - G - Bia Group. Variances in test values can occur in different production lots.

Usage recommendations

Anatolia's recommendations for suitable applications.

Usage Recommendations*, Warm White, Mica, Smoke, Charcoal		MATTE UNGLAZED PORCELAIN	
APPLICATION		WALL	FLOOR
INTERIOR	RESIDENTIAL	•	ID, IW
	COMMERCIAL	•	ID, IW
	HEAVY COMMERCIAL	•	ID, IW
EXTERIOR	RESIDENTIAL / COMMERCIAL	•	

* These recommendations are not defined by ANSI/ISO standards.

DCOF Classifications per ANSI A326.3: (ID): Interior, Dry (IW): Interior, Wet (IW+): Interior, Wet Plus (EW): Exterior, Wet (O/G): Oils/Greases

* Factors other than the noted DCOF result must also be taken into consideration. Such factors include, but are not limited to, expected contaminants, drainage, surface texture, effect of structure on the DCOF measurement, number of grout joints, traction-enhancing features, and intended use in addition to the other criteria noted in standard ANSI A326.3